





04384 - EPOFAN PRIMER R-EC GRIGIO



1000 ml +
500 ml +
250-500 ml


Pot life at 20° C:
2-8 hours



20-30" FC 4
at 20° C



Ø 1,8-2 mm
3,5-4,5 Bar
HVLP:
Ø 1,6-1,8 mm
2-2,5 Bar
N° of coats: 2



Air drying at 20°C
12-24 hours
Low bake:
30-40 min at 70-80° C
60-90 min at 50-60° C

DESCRIPTION

Grey two-pack primer based on epoxy resins and anticorrosive non-polluting pigments.

USE

Primer suitable for all metallic surfaces and for fibreglass (GFRP).

CHARACTERISTICS

- Suitable as an anticorrosive primer under polyester putties
- Excellent adhesion to stainless steel, aluminium, light alloys, zinc coated sheets, concrete.
- High anti-corrosive power
- Good filling power
- The product may be used without sanding in "wet-on-wet" systems (with 00103 EPOFAN R-EC HARDENER W/W)
- Chromate- and lead-free
- Sealer for thermoplastic lacquers

SUBSTRATE PREPARATION

Carbon steel, stainless steel, aluminium and light alloys, hot dip galvanized steel sheet. Sand and degrease with 00695 SILICONE REMOVER SLOW.

Galvanized steel sheets: degreased with 00695 SILICONE REMOVER SLOW.

APPLICATION

Spraying.

Mixing ratio:

a) For general use, preferably in case of low baking, prepare the following mixture:

	volume	weight
04384 EPOFAN PRIMER R-EC GRIGIO	1000 ml	1000 g
00305 EPOFAN R-EC HARDENER	500 ml	300 g
00535 EPOFAN THINNER or 00556 LECHSYS EPODUR PF THINNER *	250 - 500 ml	150 - 300 g

***for extra-EEC countries only**

Pot life: 6 - 8 hours at 20 °C

b) For “wet-on-wet” systems:

	volume	weight
04384 EPOFAN PRIMER R-EC GRIGIO	1000 ml	1000 g
00103 EPOFAN R-EC HARDENER W/W	500 ml	300 g
00535 EPOFAN THINNER or 00556 LECHSYS EPODUR PF THINNER * or 00544 EPOFAN THINNER SLOW **	250 - 500 ml	150 - 300 g

*for extra-EEC countries only

** Special product – Available upon request

Pot life: 4 hours at 20 °C

c) In winter use the product at average temperatures of 12-13°C in the following mixture:

	volume	weight
04384 EPOFAN PRIMER R-EC GRIGIO	1000 ml	1000 g
00451 EPOFAN R-EC HARDENER FAST	500 ml	300 g
00535 EPOFAN THINNER or 00556 LECHSYS EPODUR PF THINNER *	250 - 500 ml	150 - 300 g

*for extra-EEC countries only

The film obtained with this mixture may be overcoated through “wet-on-wet” system.

Pot life: 2 hours at 20 °C

Spray viscosity: 20 - 30” FC4

Ø Air cap: 1,8 - 2 mm; HVLP 1,6 - 1,8 mm

Air pressure: 3,5 – 4,5 Atm; HVLP 2 - 2,5 Atm

N° of coats: 2 normal

Recommended film thickness: 80-100 µ

Coverage (theoretic value): 1l mixture = 7,4 m² at 50 µ

1 kg mixture = 6,2 m² at 50 µ

DIR 2004/42/CE: Primer IIB/c – VOC ready for use 540 g/l

This product ready for use contains at most 540 g/l VOC

DRYING TIME

a) With **00305 EPOFAN R-EC HARDENER**

- Air drying: at not less than 20 °C sand after 12 - 24 hours

- Low bake: at 70 - 80 °C sand after 30 - 40 min.

at 50 - 60 °C sand after 60 - 90 min.

b) With **00103 EPOFAN R-EC HARDENER W/W (for wet-on-wet process)**

Wait at least 30 - 40 min. at 20 °C prior to applying/reapplying the finishing topcoat.

c) With **00451 EPOFAN R-EC HARDENER FAST (hardener for low temperatures)**

Flash-off and drying times depend on the temperature. Generally the enamel or the sealing coat may be overapplied through “wet-on-wet” system after 2 hours at 12°C, while sanding may occur after 24 hours at 12-13°C.

OVERCOAT WITH

Two-pack fillers and topcoats from the Lechler range.

It cannot be overapplied on synthetic anti-rust paints.

NOTES

As for all epoxy products, EPOFAN PRIMER R-EC GRIGIO 04384 catalysed with HARDENERS 00305 and 00103 **must not be** air dried at temperatures below 15 °C.

Under this temperature a through-hardening cannot be achieved and as a consequence some defects in the painting system may occur.

HARDENER 00451 is not recommended in summer as the pot-life is reduced to a few minutes.

TECHNICAL DATA SHEET N° 0197-GB

UPDATED 09/2018

All information contained in this data sheet is the result of carefully controlled tests and is correct to the best of Lechler's knowledge at the time of issue. Since conditions of use are beyond the control of the manufacturer, information contained herein is without warranty, implied or otherwise, and final determination of the suitability of any information or material for the use contemplated and the manner of use is the sole responsibility of the user. FOR PROFESSIONAL USE ONLY.